

STYROFOAM™ LBH-X



Designation Code		XPS - EN 13164 - T3 - CS(10\Y)300 - DS(TH) - TR400			
Properties ¹⁾	Standard	STYROFOAM LBH-X	Unit	CE-Code	
Cell content		HFC			
Density	BS EN 1602	33	kg/m ³	-	
Thermal conductivity declared (λ_p)	BS EN 13164	0,033	W/m-K	-	
Compressive stress or compressive strength @ 10% deformation ²⁾	BS EN 826	0,3	N/mm ² ³⁾	CS(10\Y) σ_m	
E-Modulus (typical) ²⁾	BS EN 826	12	N/mm ²	-	
Tensile strength ²⁾	BS EN 1607	0,5	N/mm ²	TR400	
Tensile Modulus (typical) ²⁾	BS EN 1607	24 (≥ 50 mm)	N/mm ²	-	
Shear strength	BS EN 12090	0,25	N/mm ²	-	
Shear Modulus (typical)	BS EN 12090	10	N/mm ²	-	
Water vapour diffusion resistance factor μ	BS EN 12086	100	-	-	
Long term water absorption by total immersion	BS EN 12087	$\leq 1,5$	Vol-%	WL(T)1,5	
Dimensional stability under specified temperature and humidity	BS EN 1604	≤ 2	%	DS(TH)	
Capillarity	-	0	-	-	
Coefficient of linear thermal expansion	-	0,07	mm/m-K	-	
Reaction to fire Euroclass	BS EN 13501-1	E	-	-	
Temperature limits	-	-50/+75	°C	-	
Dimensions	BS EN 823 BS EN 822	upon request	-	-	
Tolerances	Thickness	BS EN 823	$\pm 0,5$	mm	T3
	Width < 700 mm	BS EN 822	-0/+3	mm	-
	Width \geq 700 mm	BS EN 822	-0/+5	mm	-
	Length	BS EN 822	-0/+10	mm	-
Edge Profile	-	butt edge	-	-	
Surface Finish	-	planed	-	-	

¹⁾ The properties refer to thickness ranges mentioned in the table.

²⁾ measured in thickness direction

³⁾ 1 N/mm² = 10³ kPa; 1 kPa = 10⁻³ Mpa

Note:

The information and data contained in this technical data sheet do not represent exact sales specifications. The features of the products mentioned may vary. The information contained in this document has been provided in good faith, however it does not imply any liability, guarantee or assurance of product performance. It is the purchaser's responsibility to determine whether these Dow products are suitable for the application desired and to ensure that the site of work and method of application conform with current legislation. No licence is hereby granted for the use of patents or other industrial or intellectual property rights. If Dow products are purchased, we advise following the most up-to-date suggestions and recommendations.

®™ Trademark of The Dow Chemical Company ("Dow") or an affiliated company of Dow

Wet Rooms Direct

Tel: 01685 898110

Email: sales@wetroomsdirect.net

Web: www.wetroomsdirect.net